

Technical Data Sheet for SPC: 228*1800*7.5mm

Property	Test method standard	Review in accordance with standard
-Wear layer	EN-ISO 24340	0.55mm
-Total thickness	EN-ISO 24346	7.5mm
-Slip resistance	DIN 51130	R9
-Emission of formaldehyde	EN 717-1	E1
-Reaction to fire	EN 13501-1/EN 13501-1	Bfl-s1
-Abrasion resistance class	EN 13329 Annex E	Group T
-Resistance to pressure	EN ISO 10582:2018 (ISO 10582:2017)	≤ 0.1mm
-Dimension stability	EN-ISO 23999	≤0.02%
-Non-slip parameter	EN 13893	DS
-Content of pentachlorophenol	EN 14041 Anex B	not found
-Utility class	EN-ISO 10582	Type 1
-Chemical resistance	EN 423:2001 or EN ISO 26987:2012	Index 0 (very good)
-Color fastness to artificial light	EN ISO 105-B02	≥ 6
- Castors resistance	EN 425:2002 (type W - 25000 cycles)	no damage in the wear layer, no delamination